

PETROGARD™ VI

	STANDARD	METRIC
Base Fabric Type P	Polyester	Polyester
Base Fabric Weight (nominal)	7.5 oz/yd ²	254 g/m ²
Coating Type T	ri-polymer alloy T	ri-polymer alloy
Thickness ASTM D751	32 ± 2 mil 0	.81 ± 0.05 mm
Weight 3 ASTM D751	0 oz/yd ² ± 2 oz/yd ²	1017 g/m ² ± 70 g/m ²
Grab Tensile ASTM D751	650/650 lb	2893/2893 N
Strip Tensile ASTM D751 Procedure B	485/485 lb/in	425/425 daN/5 cm
Low Temperature ASTM D2136	1/8 in mandrel, 4 hr Pass @ -40° F	3 mm mandrel, 4 hr Pass @ -40° C
Adhesion ASTM D751 Dielectric Weld	15 lb/in 1	3 daN/5 cm
Dead Load ASTM D751 1	2 in. seam, 4 hr, 1 in strip 266 lb @ 70° F 33 lb @ 160° F	50 mm seam, 4 hr, 25 mm strip 1184 N @ 21° C 592 N @ 71° C
Bursting Strength ASTM D751 (Ball Tip) 9	50 lb	4228 N
Hydrostatic Resistance ASTM D751 Procedure A	800 psi 5	.52 MPa
Blocking Resistance ASTM D751 # 180°F/82°C	2 rating (max.) #	2 rating (max.)
Weathering Resistance ASTM G23 (Carbon-Arc)	8000 hrs (minimum) - No appreciable changes or stiffening or cracking of coating	